



Sauerstoffundurchlässige Silofolie

Grün - Weiss



produced by



Vertrieb in Deutschland durch



Eigenschaften

	<u>Wert</u>	<u>Einheit</u>	<u>Methode</u>
Reißkraft			
Längs.	30	MPa	EN ISO 527
Quer	30	MPa	EN ISO 527
Reißdehnung			
Längs	500	%	EN ISO 527
Quer	500	%	EN ISO 527
Reißfestigkeit			
Längs	15	MPa	EN 13206
Quer	15	MPa	EN 13206
Dart Test F50			
Fläche	600	g	ISO 7765
Sauerstoffdurchlässigkeit (OTR)	< 2	cm ³ /m ² /day/0,2bar	DIN 53380
UV Beständigkeit 100 kIY	15	Monate	

All the data contained in this Specification Sheet has been obtained through our own experience and is offered at an informative level. They are obtained under optimal process conditions and therefore may vary depending on product dimensions, extruding equipment, etc. SOLPLAST S.A. reserves the right to change these data at any time without notice. These data are given with all the goodwill but as the circumstances and conditions upon which this information could be used are beyond our control, we cannot accept any responsibility for any lost or damage caused by its use.