

**Product Description:**
**LLDPE Film – White – 1280 or 1380 in 16  $\mu$** 

	UNITS	TOLERANCES	AVERAGE VALUES	TESTING METHOD
<b>Dimensions:</b>				
Average Thickness:	Microns $\mu$	$\pm 8 \%$	16	UNE EN ISO 4593
Puntual Thickness	Microns $\mu$	$\pm 30 \%$	16	UNE EN ISO 4593
Length:	m	$\pm 5 \%$	2.000	
<b>Mechanical features:</b>				
Tensile strength at break MD	N	-10%	38	UNE- EN ISO 527-3
Tensile strength at break TD	N	-10%	8,8	UNE- EN ISO 527-3
Elongation at break: MD	%	-10%	80	UNE EN ISO 527-3
Elongation at break: TD	%	-10%	660	UNE EN ISO 527-3
Tear Resistance MD	mN	-10%	700	UNE- EN ISO 6383-2
Tear Resistance TD	mN	-10%	4500	UNE- EN ISO 6383-2
Impact resistance - Dart test	gr	-10%	150	UNE -EN ISO 7765-1
U.V. Stabilisation	months	0	Film has to be protected from direct sunlight	

MD : machine direction

TD: Transversal direction